



# ARAMID PACKING K6600C

## Composition

The K6600C packing is made with continuous thermostable aramid yarns. Each yarn is impregnated with PTFE dispersion and silicon free inert lubricant. Suitable for use on centrifugal and piston pumps with very abrasive fluids. Low shaft's speed or shaft's protection is needed.

## Characteristics

Continuous aramid yarns  
PTFE impregnation  
Lubricant silicon free

## Applications

Packing for pumps suitable with abrasive fluids

## Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T °C	T °F
	100	1500	3	600	3 ÷ 12	-100 ÷ 280	-150 ÷ 540
	20	300	15	3000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



## Aramid Packing K6600C

The braided packing for pumps K6600C is made with continuous aramid yarns



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

 **CARRARA**  
GLOBAL SEALING SOLUTIONS

**Carrara S.p.A.**,  
Via Provinciale 1/E - 25030 Adro - BS - Italia  
tel. +39 030 7451121 / fax +39 030 7451130  
[www.carrara.it](http://www.carrara.it) - [info@carrara.it](mailto:info@carrara.it)



# ARAMID PACKING K6600C

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	74.1	243	74.1	110.3
4	-	1	2.2	41.7	137	41.7	62.1
5	3/16	1	2.2	26.7	87	26.7	39.7
6	-	2.5	5.5	46.3	152	18.5	27.6
6.5	1/4	2.5	5.5	39.4	129	15.8	23.5
8	5/16	2.5	5.5	26	85	10.4	15.5
9.5	3/8	2.5	5.5	18.5	61	7.4	11
10	-	2.5	5.5	16.7	55	6.7	9.9
11	7/16	2.5	5.5	13.8	45	5.5	8.2
12	-	2.5	5.5	11.6	38	4.6	6.9
12.7	1/2	2.5	5.5	10.3	34	4.1	6.2
14	9/16	5	11	17	56	3.4	5.1
16	5/8	5	11	13	43	2.6	3.9
17.5	11/16	5	11	10.9	36	2.2	3.2
18	-	5	11	10.3	34	2.1	3.1
19	3/4	5	11	9.2	30	1.8	2.8
22	7/8	5	11	6.9	23	1.4	2.1
25.5	1	5	11	5.1	17	1	1.5

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

**CARRARA**  
GLOBAL SEALING SOLUTIONS

**Carrara S.p.A.**,  
Via Provinciale 1/E - 25030 Adro - BS - Italia  
tel. +39 030 7451121 / fax +39 030 7451130  
[www.carrara.it](http://www.carrara.it) - [info@carrara.it](mailto:info@carrara.it)