



ARAMID PACKING KD6605

Composition

Discontinuous aramid fibres
PBI yarns on the corners
PTFE and lubricant impregnation



Characteristics

Special compression packing made with aramid yarns; corners are further reinforced using PBI yarns. The impregnation is done in three stages: first on the yarns, secondly during the braiding and thirdly on the surface of the finished product. The special aramid gland compression packing KD6605 DINACOMB® is made with aramid and PBI yarns that reduces the coefficient of friction. The impregnation, that comes in three steps, on the yarns, during the braiding and on the body, gives to the packing great flexibility and wear resistance.

Applications

KD6605 is a highly performing sealing product, ideal for use in pumps, pulpers, and mixers used in various industrial sectors, such as paper, sugar, and cement. This aramid fiber packing ensures an excellent level of sealing, allowing the control of leaks and preventing fluid leakage. This product has been specially designed to reduce the frequency of maintenance operations, thanks to its high resistance and reliability. In this way, maintenance costs are reduced and plant productivity is increased. KD6605 is the ideal choice for those looking for a high-quality sealing solution that guarantees excellent performance, long life, and low maintenance costs.

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	80	1200	2	400	3 ÷ 12	-100 ÷ 250	-150 ÷ 480
	30	450	20	4000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



Aramid Packing KD6605

The range of aramid fiber products includes a wide selection of braids and packings that can be used in numerous applications requiring the use of this material. Aramid fiber yarn, both continuous and discontinuous, is used alone or in combination with other technical yarns to produce packings for gland sealing systems, both for static and dynamic applications. The properties of aramid fiber allow for efficient, reliable sealing that can cover a pH range of 3 to 12. Aramid fiber products are available in both dry and lubricated versions and can be combined with other fibers, such as GFO, PTFE, and PBI, or with a rubber core.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

 **CARRARA**
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



ARAMID PACKING KD6605

size mm	size inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	74.1	243	74.1	110.3
4	-	1	2.2	41.7	137	41.7	62.1
5	3/16	1	2.2	26.7	87	26.7	39.7
6	-	2.5	5.5	46.3	152	18.5	27.6
6.5	1/4	2.5	5.5	39.4	129	15.8	23.5
8	5/16	2.5	5.5	26	85	10.4	15.5
9.5	3/8	2.5	5.5	18.5	61	7.4	11
10	-	2.5	5.5	16.7	55	6.7	9.9
11	7/16	2.5	5.5	13.8	45	5.5	8.2
12	-	2.5	5.5	11.6	38	4.6	6.9
12.7	1/2	2.5	5.5	10.3	34	4.1	6.2
14	9/16	5	11	17	56	3.4	5.1
16	5/8	5	11	13	43	2.6	3.9
17.5	11/16	5	11	10.9	36	2.2	3.2
18	-	5	11	10.3	34	2.1	3.1
19	3/4	5	11	9.2	30	1.8	2.8
22	7/8	5	11	6.9	23	1.4	2.1
25.5	1	5	11	5.1	17	1	1.5

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it