



ARAMID PACKING PA3604

Composition

The packing for pumps PA3604 is made with 100% meta aramid yarns impregnated with pure P.T.F.E. and lubricant silicon free. The coefficient of friction of this packing is lower than the para aramid packing with equivalent yarn's tensile strength. This compression packing is suitable for any dynamic applications with abrasive fluids with which the meta aramid yarns are compatible.



Characteristics

Meta aramid fibres
PTFE impregnation
Lubricant silicon free

Applications

Pump aramid packing

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	80	1200	2	400	1 ÷ 13	-100 ÷ 250	-150 ÷ 480
	20	300	15	3000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



Aramid Packing PA3604

The packing for pumps PA3604 is made with 100% meta aramid yarns impregnated with pure P.T.F.E. and lubricant silicon free.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



ARAMID PACKING PA3604

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	74.1	243	74.1	110.3
4	-	1	2.2	41.7	137	41.7	62.1
5	3/16	1	2.2	26.7	87	26.7	39.7
6	-	2.5	5.5	46.3	152	18.5	27.6
6.5	1/4	2.5	5.5	39.4	129	15.8	23.5
8	5/16	2.5	5.5	26	85	10.4	15.5
9.5	3/8	2.5	5.5	18.5	61	7.4	11
10	-	2.5	5.5	16.7	55	6.7	9.9
11	7/16	2.5	5.5	13.8	45	5.5	8.2
12	-	2.5	5.5	11.6	38	4.6	6.9
12.7	1/2	2.5	5.5	10.3	34	4.1	6.2
14	9/16	5	11	17	56	3.4	5.1
16	5/8	5	11	13	43	2.6	3.9
17.5	11/16	5	11	10.9	36	2.2	3.2
18	-	5	11	10.3	34	2.1	3.1
19	3/4	5	11	9.2	30	1.8	2.8
22	7/8	5	11	6.9	23	1.4	2.1
25.5	1	5	11	5.1	17	1	1.5

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it