



C8200

Composition

Pre-oxidized PAN carbon yarns with impregnation of graphite and passive corrosion inhibitor. _x000D_

Characteristics

C8200 is the compression packing made with PAN pre-oxidized carbon yarns. The packing, easy to cut and install, is impregnated strand by strand with a special colloidal graphite compound for giving to its body extreme compactness and flexibility. It is also available in the style C8300R with metal reinforcement.

Applications

C8200 is a versatile packing that can be used both for all static and dynamic services in the presence of steam, air, gas, oils, bitumen, petroleum and chemical products with the exception of those oxidizing and not compatible with graphite.

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T °C	T °F
	150	2250	1	20			
	100	150	2	40	2 ÷ 12	-50 ÷ 350 / 500	-58 ÷ 662 / 940
	20	300	20	400			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- Graphite and carbon cannot be used with oxidizing fluids



C8200

C8200 is a compression packing mainly for valve services in medium-high temperature with steam and hydrocarbons. It can also be used to seal the dynamic applications.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



C8200

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	101	331	101	150.5
4	-	1	2.2	56.8	186	56.8	84.6
5	3/16	1	2.2	36.4	119	36.4	54.2
6	-	2.5	5.5	63.1	207	25.3	37.6
6.5	1/4	2.5	5.5	53.8	176	21.5	32
8	5/16	2.5	5.5	35.5	117	14.2	21.2
9.5	3/8	2.5	5.5	25.2	83	10.1	15
10	-	2.5	5.5	22.7	75	9.1	13.5
11	7/16	2.5	5.5	18.8	62	7.5	11.2
12	-	2.5	5.5	15.8	52	6.3	9.4
12.7	1/2	2.5	5.5	14.1	46	5.6	8.4
14	9/16	5	11	23.2	76	4.6	6.9
16	5/8	5	11	17.8	58	3.6	5.3
17.5	11/16	5	11	14.8	49	3	4.4
18	-	5	11	14	46	2.8	4.2
19	3/4	5	11	12.6	41	2.5	3.8
22	7/8	5	11	9.4	31	1.9	2.8
25.5	1	5	11	7	23	1.4	2.1

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it