



CARBON PREOX PACKING N2609

Composition

Preox/Viscose yarns
Graphite Powder
Lubricant silicon free

Characteristics

CARRARA N 2609 has been developed for the purpose applications, offering a packing with very competitive price. Made with a blending of pre oxidized carbon and organic yarns, the packing is impregnated with graphite powder and lubricated with inert lubricant silicon free for high temperatures

Applications

Suitable for purpose applications with steam and mild industrial fluids

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	60	900	1	200	4 ÷ 10	-50 ÷ 250	-60 ÷ 480
	40	600	3	600			
	20	300	10	2000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



Carbon Preox Packing N2609

N2609 is a general-purpose packing at a very affordable price. It is made from a composite synthetic fiber in the intermediate stage of carbon pre-oxidation, with graphite-based impregnation and a high-temperature lubricant that is silicone-free.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



CARBON PREOX PACKING N2609

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8"	1	2.2	100.0	328.1	100.0	149.0
4	-	1	2.2	50.0	164.0	50.0	74.5
5	3/16"	1	2.2	33.3	109.3	33.3	49.6
6	-	2.5	5.5	50.0	164.0	20.0	29.8
6.5	1/4"	2.5	5.5	45.5	149.3	18.2	27.1
8	5/16"	2.5	5.5	31.3	102.7	12.5	18.7
9.5	3/8"	2.5	5.5	22.7	74.5	9.1	13.5
10	-	2.5	5.5	20.8	68.2	8.3	12.4
11	7/16"	2.5	5.5	16.7	54.8	6.7	10.0
12	-	2.5	5.5	14.7	48.2	5.9	8.8
12.7	1/2"	2.5	5.5	13.9	45.6	5.6	8.3
14	9/16"	5	11	21.7	71.2	4.3	6.5
16	5/8"	5	11	16.1	52.8	3.2	4.8
17.5	-	5	11	14.3	46.9	2.9	4.3
18	11/16"	5	11	12.5	41.0	2.5	3.7
19	3/4"	5	11	11.6	38.1	2.3	3.5
22	7/8"	5	11	8.6	28.2	1.7	2.6
25.5	1"	5	11	6.7	22.0	1.3	2.0

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it