



COMPRESSED FIBER GASKETS PLANIFLEX™ PF41

Composition

Organic fiber NBR binder.

Characteristics

The compressed fiber gasketing sheets Planiflex™ PF41 are the greatest material for general applications. Economic, secure, tested.

Applications

Planiflex™ PF41 can be applied continuously in the temperature range $-40^{\circ}\text{C} \div 120^{\circ}\text{C}$ and in the pressure ranges up to ratings 600 lbs and PN40. These gaskets show typical chemical compatibility in the middle of the pH range.

Tech Data

| Properties thickness 1,5 mm | Unit | Value |
|---|-------|-------|
| Binder | -- | NBR |
| Compressibility ASTM F 36 | % | 9 |
| Recovery ASTM F 36 | % | 60 |
| Tensile strength DIN 52910 | N/mm2 | 8 |
| Density +/- 5% | g/cm3 | 1,8 |
| Stress resistance DIN 52913 | | |
| 16 h, 300 °C, 50 N/mm2 | N/mm2 | -- |
| 16 h, 175 °C, 50 N/mm2 | N/mm2 | 20 |
| Thickness increase acc.to ASTM F 146 | | |
| Oil IRM 903, 5 h, 150 °C | % | 10 |
| ASTM Fuel B, 5 h, 23 °C | % | 10 |
| Distilled water. 5h. 100°C | % | 4 |
| Max. operating conditions | | |
| Peak temperature | °C | 180 |
| Continuous temperature | °C | 140 |
| Continuous temperature with steam | °C | 120 |
| Pressure | bar | 40 |

- The peak temperature can be sustained for short exposures
- Do not use the product at maximum temperature values or under pressures higher than those typical of flue gases. Consult the manufacturer for further information.

| | | |
|-----------|--------------------------------|-------------------------|
| Size | 1.500 x 1.500 1.500 x 3.000 | 60" x 60" 60" x 120" |
| Thickness | 0.5 ÷ 5.0 | 1/64" ÷ 7/32" |



Compressed fiber gaskets Planiflex™ PF41

The Planiflex™ gasketing sheets are made with materials based on aramid fibers and NBR specially selected for meet high performance standards for a wide range of industrial applications. Planiflex™ gaskets are applicable for seal with vapors, lubricants, solvents, gases, steam and many diluted acids and alkalis and can be used as a gasket together with PTFE envelopes.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it