

## Composition

Reinforced graphite packing made with preformed rings of **GR80SGR** type flexible graphite braided gland packing

### **Characteristics**

The **CONTROLLER 3 EVO** expanded graphite is a packing for industrial valves. The GR80SGR packing ensures high performance in operation across the full temperature range, while offering a low coefficient of friction.

CONTROLLER 3 EVO, certified for Low Emission according to ISO 15848 BH-CO1, maintains its elasticity and sealing properties over time, ensuring safe valve operation.



# **CONTROLLER 3 EVO**

Graphite stem sealing packing for industrial valves, made with expanded graphite sealing rings for Low Emissions services, approved according to ISO 15848 BH-C01.

#### Applications

CONTROLLER 3 EVO is specifically designed for industrial valves in Low Emission services according to ISO 15848 BH-C01. It is also suitable for HP/HT steam services and hydrogen applications.

#### **Tech Data**



Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information

- The peak temperature can be sustained for short exposures •
- With weakly oxidizing agents and hot air the temperature must be limited to 450  $^\circ$  C With steam and non-oxidizing fluids the temperature must be limited to 650  $^\circ$  C
- Graphite and carbon cannot be used with oxidizing fluids



#### Carrara S.p.A.,

Via Provinciale 1/E - 25030 Adro - BS - Italia tel. +39 030 7451121 / fax +39 030 7451130 www.carrara.it - info@carrara.it



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.