



GASKETING SHEET PLANIFLEX™ PF63

Composition

Aramid fibres and NBR binder

Characteristics

The compressed fiber gaskets Planiflex™ PF63 are a material with an excellent sealing performance, usable with oils, gas, fuel. Planiflex™ PF63 shows excellent stress retention properties and excellent sealing performance.

Applications


Planiflex™ PF63 can be applied continuously in the temperature range $-40^{\circ}\text{C} \div 180^{\circ}\text{C}$ and in the pressure ranges up to ratings 600 lbs and PN40. These gaskets show chemical compatibility in the pH range typical of that of nitrile rubbers.

Tech Data

Properties thickness 1,5 mm	Unit	Value
Compressibility ASTM F 36	%	11
Recovery ASTM F 36	%	50
Tensile strength DIN 52910	N/mm2	6
Density +/- 5%	g/cm3	1,9
Stress resistance DIN 52913		
16 h, 175 °C, 50 N/mm2	N/mm2	25
Thickness increase acc.to ASTM F 146		
Oil IRM 903, 5 h, 150 °C	%	12
ASTM Fuel B, 5 h, 23 °C	%	10
Max. operating conditions		
Peak temperature	°C	250
Continuous temperature	°C	180
Continuous temperature with steam	°C	150
Pressure	bar	50

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- The dimensional tolerances of the gasketing sheets are: W and L $\pm 3,0\%$, H $\pm 10,0\%$

Size	1.500 x 1.500 1.500 x 3.000	60"x60" 60"x120"
Thickness	0,4 ÷ 5,0	1/64" ÷ 7/32"



Gasketing sheet Planiflex™ PF63

The Planiflex™ gasketing sheets are made with materials based on aramid fibers and NBR specially selected for meet high performance standards for a wide range of industrial applications. Planiflex™ gaskets are applicable for seal with vapors, lubricants, solvents, gases, steam and many diluted acids and alkalis and can be used as a gasket together with PTFE envelopes.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it