



GLASS FIBRE PACKING V9907

Composition

The Glass fiber packing V9907 is made with E glass yarns impregnated with a special compound of graphite. It's also available in the style Inconel wire V9907R. Packing suitable for static and dynamic application. Suitable too for man lid or with combusted gases. Not suitable with high temperature steam.



Characteristics

E glass fibre
Impregnation with graphite and PTFE
Lubricated

Applications

Glass fiber packing for general use

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T °C	T °F
	200	3000	2	300	2 ÷ 12	-50 ÷ 500	-60 ÷ 940
	10	150	5	1000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



Glass Fibre Packing V9907

The Glass fiber packing V9907 is made with E glass yarns impregnated with a special compound of graphite. It's also available in the style Inconel wire V9907R.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



GLASS FIBRE PACKING V9907

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	74.1	243	74.1	110.3
4	-	1	2.2	41.7	137	41.7	62.1
5	3/16	1	2.2	26.7	87	26.7	39.7
6	-	2.5	5.5	46.3	152	18.5	27.6
6.5	1/4	2.5	5.5	39.4	129	15.8	23.5
8	5/16	2.5	5.5	26	85	10.4	15.5
9.5	3/8	2.5	5.5	18.5	61	7.4	11
10	-	2.5	5.5	16.7	55	6.7	9.9
11	7/16	2.5	5.5	13.8	45	5.5	8.2
12	-	2.5	5.5	11.6	38	4.6	6.9
12.7	1/2	2.5	5.5	10.3	34	4.1	6.2
14	9/16	5	11	17	56	3.4	5.1
16	5/8	5	11	13	43	2.6	3.9
17.5	11/16	5	11	10.9	36	2.2	3.2
18	-	5	11	10.3	34	2.1	3.1
19	3/4	5	11	9.2	30	1.8	2.8
22	7/8	5	11	6.9	23	1.4	2.1
25.5	1	5	11	5.1	17	1	1.5

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it