



GRAPHITE RING ZV48Z OXY BAM APPROVED

Composition

Pure flexible graphite

Characteristics

ZV48Z OXY rings ensure safe and reliable performance in environments with liquid and gaseous oxygen. Certified according to BAM specifications, they provide effective protection against oxidation. When used in stems, assistance from ZGR80SGR OXY braided wiper rings (BAM report 2-28/2015E) or ZV48ZN OXY nickel-reinforced graphite rings (BAM report 2-1948/2014E) is recommended.

Applications

Made with highly pure graphite, ZV48Z OXY expanded graphite rings offer high quality and reliability for applications involving liquid and gaseous oxygen.

Tech Data

Maximum Temperature C°	Maximum Oxygen Pressure bar
up to 60	420
> 60 to 280	250

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- Carrara S.p.A., Via Provinciale 1/E 25030 Adro - BS - Italia - tel. +39 030 7451121 - fax +39 030 7451130 - <http://www.carrara.it> - info@carrara.it



Report
on Testing a Nonmetallic Material for Reactivity with Oxygen

Reference Number 2-1949/2014 E
Copy 1. Copy of 2 Copies
Customer CARRARA S.p.A.
Via Provinciale, 1/E
25030 Adro (BS)
Italia
Order Date August 4, 2014
Reference Order No.: 1411295
Receipt of Order August 11, 2014
Test Samples Die-formed flexible graphite ring Valvograph ZV48Z OXY, undisclosed batch, for use as a sealing material in piping, valves and fittings or other components for gaseous oxygen service at temperatures up to 280 °C and for liquid oxygen service.
BAM-Order No.: 2-1952/220
Receipt of Samples August 7, 2014
Test Date August 22, 2014 to February 6, 2015
Test Location BAM - Working Group "Safe Handling of Oxygen", building no. 41, room no. 073 and no. 120
Test Procedure or Requirement According to DIN EN 1797:2002-02
"Cryogenic Vessels - Gas/Material Compatibility"
ISO 21010:2004-07
"Cryogenic Vessels - Gas/Material Compatibility"
Annex of pamphlet M 034-1 (BGI 617-1)
"List of nonmetallic materials compatible with oxygen by BAM Federal Institute for Material Research and Testing", by Berufsgenossenschaft Robotik und chemische Industrie, Edition: March 2014.
TRGS 407 Technical Rules for Hazardous Substances "Tätigkeiten mit Gasen - Gefährdungsbeurteilung" chapter 3 "Informationsermittlung und Gefährdungsbeurteilung" and chapter 4 "Schutzmaßnahmen bei Tätigkeiten mit Gasen" Edition: June 2013

EST REPORT

Graphite ring ZV48Z OXY BAM approved

ZV48Z OXY graphite rings are BAM certified for use with both liquid and gaseous oxygen. These expanded graphite rings are designed for services involving liquid and gaseous oxygen (BAM report 2-1949/2014 E), serving for stem or as fire-safe seals for closures and as packing for ball valve seats.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it