



PLANIGRAPH™ LGRHDI

Composition

- Expanded Graphite Industrial Grade
- Multiple smooth SS316L inserts with a thickness of 0.05 mm

Characteristics

The Planigraph™ LGRHDI graphite gasketing sheets are suitable for high-temperature and high-pressure applications on RF, FF, LMF, and LTG flanges in piping or industrial machinery. Planigraph™ LGRHDI features low relaxation values combined with excellent mechanical strength.

Applications

The graphite gaskets Planigraph™ LGRHDI are suitable for all flanges, including RF, FF, LMF, and LTG. Graphite cannot be used with oxidizing fluids.

Tech Data

Planigraph™ LGRHDI

Planigraph™ LGRHDI		
Graphite density	gr/cm ³	1.0
Carbon Content	%	≥ 98.0
Ash Content	%	≤ 2.0
Sulphur Content	ppm	≤ 1000
Halogen Content	ppm	≤ 200
Reinforcing steel sheet	AISI	316L
Thickness steel sheet	mm	0.05
Tensile Strength	MPa	≥ 4.0
Compressibility	%	25 - 35
Recovery	%	> 15
Relaxation stress DIN 52913	N/mm ²	> 45
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196
Maximum assembly load RT	N/mm ²	200
Maximum operating pressure	bar	200

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.
- With steam and non-oxidizing fluids, the temperature must be limited to 550°C.
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1000 x 1000 - 1500 x 1500 mm	40"x40" - 60"x60"
Thickness	1.0 ÷ 3.0 mm	1/32" ÷ 1/8"



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.



Planigraph™ LGRHDI

The Planigraph™ sales program includes the following items Premium grade and Industrial Grade:

- LG without insert
- LGR with single smooth insert
- LGRF with single or multiple tanged inserts
- LGRHDI with multiple smooth inserts

The maximum allowable load on expanded graphite gaskets depends on the type and number of metallic inserts and is closely related to the effective sealing area. Verification requires calculating the ratio $[(De-Di)/thk]$, where **De** and **Di** are the diameters of the area actually compressed between the flanges and **thk** is the gasket thickness. The ratio must be ≥ 4 . On WN RF flanges, the gaskets can be used up to class 300 psi.

The Planigraph™ line also includes corrugated graphite tapes for maintenance:

- NG - corrugated tape in expanded mineral graphite
- NGA - adhesive corrugated tape in expanded mineral graphite



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 carrara.it - info@carrara.it