

PLANIGRAPH™ PREMIUM LGRFP

Composition

- High-purity expanded mineral graphite Premium Grade with corrosion inhibitor and oxidation retardant
- Tanged sheet SS316L

Characteristics

The expanded mineral graphite of Planigraph™ Premium LGRFP meets the requirements of the latest update of the EU directive 2011/65/EC (RoHS) and complies with the requirements of the oxidation test EN 14772 section 6.7. This type of graphite gasket ensures a reliable and durable sealing, making it an ideal option for all industrial applications, from the simplest to the most demanding.

Applications

Expanded mineral graphite is also known for its chemical resistance, making it suitable for applications involving almost all fluids except for oxidants. In addition, expanded mineral graphite gaskets can be easily cut and shaped to fit the specific needs of the application. Thanks to its high thermal resistance, expanded mineral graphite can withstand high temperatures without damage or deformation, ensuring a reliable and safe sealing.

Tech Data

Planigraph™ Premium LGRFP				
Graphite density	gr/cm3	1.0		
Carbon Content	%	≥ 99.0		
Ash Content	%	< 1.0		
Sulphur Content (before inhibitiors addition)	ppm	≤ 100		
Halogen Content (after inhibitiors addition)	ppm	≤ 100		
Thermal Weight Loss 670°C/h	%	≤ 4.0		
Inhibitor of oxidation and corrosion	-	Yes		
Reinforcing steel sheet	AISI	316L		
Thickness steel sheet	mm	0.05		
Tensile Strenght	MPa	≥ 5.0		
Compressibility	%	35 - 55		
Recovery	%	≥ 9.0		
Relaxation stress 16h, 300°C, initial stress 50 N/mm2	N/mm2	> 45		
Maximum assembly load RT	N/mm2	140		
Temperature range service	°C	-200 / 550		
Maximum operating pressure	bar	100		

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.
 Other gasketing sheet dimensions and thicknesses are available on request
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1500 x 1500	60" x 60"
Thickness	1.50 ÷ 3.0	1/16" ÷ 1/8"



Planigraph™ Premium LGRFP

The Planigraph™ sales program includes the following items Premium grade and Industrial Grade:

- LG without insert
- LGR with single smooth insert
- LGRF with single or multiple tanged inserts
- LGRHDI with multiple smooth inserts

The maximum allowable load on expanded graphite gaskets depends on the type and number of metallic inserts and is closely related to the effective sealing area. Verification requires calculating the ratio [(De–Di)/thk], where \mathbf{De} and \mathbf{Di} are the diameters of the area actually compressed between the flanges and \mathbf{thk} is the gasket thickness. The ratio must be \geq 4. On WN RF flanges, the gaskets can be used up to class 300 psi.

The Planigraph™ line also includes corrugated graphite tapes for maintenance:

- NG corrugated tape in expanded mineral graphite
- NGA adhesive corrugated tape in expanded mineral graphite



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not accurately represent the product's color and/or marking.



Carrara S.p.A.,

Via Provinciale 1/E - 25030 Adro - BS - Italia tel. +39 030 7451121 www.carrara.it - info@carrara.it