



# PBO PACKING N1704

## Composition

Synthetic yarns  
Impregnation with PTFE and solid lubricant



## Characteristics

The compression packing N1704 HP is produced by a new generation of heat-resistant yarns that exceed the aramid fiber's properties. This yarn has a resistance of 1.6 times greater than the aramid combined with high chemical inertia, excellent thermal stability and low coefficient of friction. For best results each yarn is previously impregnated with PTFE mixture and with a special solid lubricant. N1704 HP shows a surprising resistance than the conventional aramid fiber packing.

## Applications

N1704 is suitable in all application for which is normally used the aramid packing

## Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	500	7500	5	1000	1 ÷ 13	÷ 280	÷ 540
	30	450	20	4000			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



## PBO Packing N1704

N1704 is the pump compression packing made with evolved aramid yarns high resistant for heavy dynamic applications.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



**Carrara S.p.A.**,  
Via Provinciale 1/E - 25030 Adro - BS - Italia  
tel. +39 030 7451121 / fax +39 030 7451130  
[www.carrara.it](http://www.carrara.it) - [info@carrara.it](mailto:info@carrara.it)



# PBO PACKING N1704

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8"	1	2.2	71.4	234.3	71.4	106.4
4	-	1	2.2	45.5	149.3	45.5	67.8
5	3/16"	1	2.2	26.3	86.3	26.3	39.2
6	-	2.5	5.5	35.7	117.1	14.3	21.3
6.5	1/4"	2.5	5.5	33.3	109.3	13.3	19.8
8	5/16"	2.5	5.5	31.3	102.7	12.5	18.7
9.5	3/8"	2.5	5.5	21.4	70.2	8.5	12.7
10	-	2.5	5.5	19.2	63.0	7.7	11.4
11	7/16"	2.5	5.5	15.9	52.2	6.4	9.5
12	-	2.5	5.5	13.2	43.3	5.3	7.9
12.7	1/2"	2.5	5.5	11.9	39.0	4.8	7.1
14	9/16"	5	11	19.6	64.3	3.9	5.8
16	5/8"	5	11	15.6	51.2	3.1	4.6
17.5	-	5	11	13.3	43.6	2.7	4.0
18	11/16"	5	11	11.9	39.0	2.4	3.5
19	3/4"	5	11	10.7	35.1	2.1	3.2
22	7/8"	5	11	7.9	25.9	1.6	2.4
25.5	1"	5	11	6.4	21.0	1.3	1.9

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

**CARRARA**  
GLOBAL SEALING SOLUTIONS

**Carrara S.p.A.**,  
Via Provinciale 1/E - 25030 Adro - BS - Italia  
tel. +39 030 7451121 / fax +39 030 7451130  
[www.carrara.it](http://www.carrara.it) - [info@carrara.it](mailto:info@carrara.it)