PLANIFLEX™ PF64

Composition
Aramid fibres, inert filler and NBR binder

Characteristics
The compressed fiber gaskets Planiflex™ PF64 are a material with an excellent sealing performance, usable with oils, gas, fuel and inorganic acids. Planiflex™ PF64 shows excellent stress retention properties and excellent sealing performance.


Applications
Planiflex™ PF64 can be applied continuously in the temperature range -45°C÷250°C and in the pressure ranges up to ratings 600 lbs and PN40. These gaskets show chemical compatibility in the pH range typical of that of nitrile rubbers.

Tech Data

Properties thickness 1,5 mm	Unit	Value
Binder	--	NBR
Compressibility ASTM F 36	%	≥ 8
Recovery ASTM F 36	%	≥ 50
Stress relaxation ASTM F38	%	15
Specific Leakage Rate	mg/m/s	≤ 0.05
Density	g/cm3	1.7
Oil IRM 903, 5 h, 150 °C	%	≤ 10
ASTM Fuel B, 5 h, 23 °C	%	≤ 10
Hydrocarbon, 72 h, 90 °C	%	≤10
Sea Water, 72 h, 90 °C	%	≤10
Peak temperature	°C	350
Continuous temperature	°C	250
Continuous temperature with steam	°C	220
Low Temperature	°C	-45
Pressure	bar	70
Min. Gasket Seating Stress - Sgmin-$S_{L0,001}$	MPa	43
Min. Gasket Operating Stress - Sgmin-O	MPa	11
Max Gasket Operating Stress - Sgmax	MPa	200

- Never use the product at its maximum rated temperature and pressure simultaneously. Consult the manufacturer for further information.
- The peak temperature can be sustained only for short exposure periods.
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1.500 x 1.500 1.500 x 3.000	60” x 60” 60” x 120”
Thickness	0.5 ÷ 5.0	1/64” ÷ 3/16”



Planiflex™ PF64

The Planiflex™ gasketing sheets are made with materials based on aramid fibers and NBR specially selected for meet high performance standards for a wide range of industrial applications. Planiflex™ gaskets are applicable for seal with vapors, lubricants, solvents, gases, steam and many diluted acids and alkalis and can be used as a gasket together with PTFE envelopes.

The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.

CARRARA GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 carrara.it - info@carrara.it