



PLANIFLON™ SEAL TAPE

Composition

Adhesive tape in pure unidirectional expanded PTFE

Characteristics

- **Inert and resistant material:** pure ePTFE, with exceptional chemical resistance (pH 0-14) to all industrial fluids, except molten alkali metals and elemental fluorine.
- **Wide operating range:** usable from **-200 °C to +260 °C** and up to **200 bar** under controlled conditions.
- **High conformability:** easily adapts to surface irregularities and imperfections, ensuring uniform load distribution.
- **Secure sealing even under vacuum:** suitable for applications from deep vacuum to high pressures.
- **Long-term stability:** the material does not age and can be stored indefinitely; for best adhesion, use is recommended within 2 years of purchase.

Applications

The advantages of using Planiflon™ Seal Tape are multiple and simplify maintenance activities.

- Easy and quick application thanks to the **adhesive backing** which facilitates positioning on the flange.
- **Reduces plant downtime:** no pre-cutting or templates needed; just wrap, overlap the ends, and tighten the bolts.
- Compatible with **large metal flanges**, where traditional gaskets would be difficult to install.

Tech Data

Density 0.8 gr/cm ³	T°C -200/+260	pH 0-14	P bar 200
PLANIFLON™ SEAL TAPE sizes			
Code	Width (mm)	Thickness (mm)	Spool (m)
P_ST_03	3	1.5	30
P_ST_05	5	2.0	20
P_ST_07	7	2.5	15
P_ST_10	10	3.0	10
P_ST_12	12	4.0	10
P_ST_14	14	5.0	5/25
P_ST_17	17	6.0	5/25
P_ST_20	20	7.0	5/25
P_ST_25	25	8.0	5

- Other gasketing sheet dimensions and thicknesses are available on request
- PTFE is not compatible with molten alkali metals and elemental fluorine (F₂)



Planiflon™ Seal Tape

Planiflon™ Seal Tape is a highly conformable sealing tape, made of 100% expanded PTFE (ePTFE), designed to ensure reliable sealing on large flanges and uneven surfaces. Thanks to its unidirectional strength structure and easy application with adhesive backing, it represents a versatile and safe solution for numerous industrial plants.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it