



PLANIGRAPH™ LG

Composition

Pure graphite C > 98.0 %

Characteristics

The LG gasketing sheet made by pure expanded graphite are great for applications on low pressure flanges. The pure graphite has modest tensile strength and therefore it's always recommended the thickness from 0.4 to 1.0 mm for the best sealing.

Applications

Flat graphite gaskets for low pressure applications. Graphite isn't suitable for oxidizing fluids.

Tech Data

Planigraph™ LG

Graphite density	gr/cm ³	1.0
Carbon Content	%	> 98.0
Ash Content	%	< 2.0
Sulphur Content	ppm	≤ 1000
Halogen Content	ppm	≤ 200
Tensile Strength	MPa	≥ 4.0
Compressibility	%	40 - 50
Recovery	%	> 7
Relaxation stress DIN 52913	N/mm ²	> 45
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196
Maximum assembly load RT	N/mm ²	40
Maximum operating pressure	bar	40

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.
- With steam and non-oxidizing fluids, the temperature must be limited to 550°C.
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1.000 x 1.000 1.500 x 1.500	40" x 40" 60" x 60"
Thickness	0.5 ± 3.0	1/64" ± 1/8



Planigraph™ LG

The Planigraph™ sales program includes the following items Premium grade and Industrial Grade:

- LG without insert
- LGR with single smooth insert
- LGRF with single or multiple tapered inserts
- LGRHDI with multiple smooth inserts

The maximum allowable load on expanded graphite gaskets depends on the type and number of metallic inserts and is closely related to the effective sealing area. Verification requires calculating the ratio $[(De-Di)/thk]$, where **De** and **Di** are the diameters of the area actually compressed between the flanges and **thk** is the gasket thickness. The ratio must be ≥ 4 . On WN RF flanges, the gaskets can be used up to class 300 psi.

The Planigraph™ line also includes corrugated graphite tapes for maintenance:

- NG - corrugated tape in expanded mineral graphite
- NGA - adhesive corrugated tape in expanded mineral graphite



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 carrara.it - info@carrara.it