



PLANIGRAPH™ NGA ADHESIVE CORRUGATED GRAPHITE TAPE

Composition

High-purity Adhesive Corrugated Expanded Mineral Graphite Tape Industrial Grade

Characteristics

The adhesive corrugated expanded mineral graphite tape Planigraph™ NGA meets the requirements of the latest update of the EU Directive 2011/65/EC (RoHS). This type of gasket therefore ensures reliable and long-lasting sealing, making it an ideal option for many applications, from the simplest to the most demanding.

Applications

Adhesive corrugated graphite tape is a useful aid in industrial maintenance of valves and flanges. Planigraph™ NGA can be easily cut and shaped to fit the specific requirements of the application. Expanded mineral graphite is known for its chemical and thermal resistance, making it suitable for applications involving almost all fluids except oxidizing agents.

Tech Data

Planigraph™ NGA Adhesive Corrugated Tape

Graphite density	gr/cm3	1.0
Carbon Content	%	≥ 98.0
Ash Content	%	< 2.0
Sulphur Content	ppm	≤ 1000
Halogen Content	ppm	≤ 200
Tensile Strength	MPa	≥ 4.0
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196

Planigraph™ NGA Adhesive Corrugated Tape — Sizes

Code	Width (mm)	Thickness (mm)	Spool (mt)
N_NG_006.00	6.0	0.6	25
N_NG_008.00	8.0	0.6	25
N_NG_010.00	10.0	0.6	25
N_NG_012.00	12.0	0.6	25
N_NG_012.70	12.7	0.6	25
N_NG_015.00	15.0	0.6	25
N_NG_016.00	16.0	0.6	25
N_NG_019.00	19.0	0.6	25
N_NG_020.00	20.0	0.6	25
N_NG_025.00	25.0	0.6	25

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.
- With steam and non-oxidizing fluids, the temperature must be limited to 550°C.



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not accurately represent the product's color and/or marking.

Planigraph™ NGA Adhesive Corrugated Graphite Tape

The Planigraph™ sales program includes the following items Premium grade and Industrial Grade:

- LG without insert
- LGR with single smooth insert
- LGRF with single or multiple tanged inserts
- LGRHDI with multiple smooth inserts

The maximum allowable load on expanded graphite gaskets depends on the type and number of metallic inserts and is closely related to the effective sealing area. Verification requires calculating the ratio $[(D_e - D_i)/thk]$, where D_e and D_i are the diameters of the area actually compressed between the flanges and thk is the gasket thickness. The ratio must be ≥ 4 . On WN RF flanges, the gaskets can be used up to class 300 psi.

The Planigraph™ line also includes corrugated graphite tapes for maintenance:

- NG – corrugated tape in expanded mineral graphite
- NGA – adhesive corrugated tape in expanded mineral graphite



Carrara S.p.A.,

Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 www.carrara.it info@carrara.it