



# PLANIGRAPH™ PREMIUM LGP

## Composition

- High-purity expanded mineral graphite Premium Grade with corrosion inhibitor and oxidation retardant

## Characteristics

The expanded mineral graphite of Planigraph™ Premium LGP meets the requirements of the latest update of the EU directive 2011/65/EC (RoHS) and complies with the requirements of the oxidation test EN 14772 section 6.7. This type of graphite gasket ensures a reliable and durable sealing, making it an ideal option for all industrial applications, from the simplest to the most demanding.

## Applications

Expanded mineral graphite is also known for its chemical resistance, making it suitable for applications involving almost all fluids except for oxidants. In addition, expanded mineral graphite gaskets can be easily cut and shaped to fit the specific needs of the application. Thanks to its high thermal resistance, expanded mineral graphite can withstand high temperatures without damage or deformation, ensuring a reliable and safe sealing.

## Tech Data

Planigraph™ Premium LGP		
Graphite density	gr/cm3	1.0
Carbon Content	%	≥ 99.0
Ash Content	%	< 1.0
Sulphur Content	ppm	≤ 100
Halogen Content	ppm	≤ 100
Inhibitor of oxidation and corrosion	-	Yes
Thermal Weight Loss 670°C/h	%	≤ 4.0
Tensile Strength	MPa	≥ 4.0
Compression ratio	%	40 - 50
Recovery	%	> 7
Gas Permeability DIN 3535	cm3/min	< 1.0
Relaxation stress DIN 52913	N/mm2	> 45
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196
Maximum assembly load RT	N/mm2	40
Maximum operating pressure	bar	40

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.
- Other gasketing sheet dimensions and thicknesses are available on request.
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1500 x 1500	60" x 60"
Thickness	0.8 ÷ 3.0	1/32" ÷ 1/8"



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.



## Planigraph™ Premium LGP

The Planigraph™ sales program includes the following items Premium grade and Industrial Grade:

- LG without insert
- LGR with single smooth insert
- LGRF with single or multiple tapered inserts
- LGRHDI with multiple smooth inserts

The maximum allowable load on expanded graphite gaskets depends on the type and number of metallic inserts and is closely related to the effective sealing area. Verification requires calculating the ratio  $[(De-Di)/thk]$ , where **De** and **Di** are the diameters of the area actually compressed between the flanges and **thk** is the gasket thickness. The ratio must be  $\geq 4$ . On WN RF flanges, the gaskets can be used up to class 300 psi.

The Planigraph™ line also includes corrugated graphite tapes for maintenance:

- NG - corrugated tape in expanded mineral graphite
- NGA - adhesive corrugated tape in expanded mineral graphite



**Carrara S.p.A.**  
Via Provinciale 1/E - 25030 Adro - BS - Italia  
tel. +39 030 7451121 [carrara.it](http://carrara.it) - [info@carrara.it](mailto:info@carrara.it)