

Composition

- Expanded graphite rings with high purity C > 99%.
- Top & Bottom rings made of carbon yarn reinforced with Ni-Cr discontinuous microfilaments, Incobraid® GR8807 type.

Characteristics

The Incobraid® PLANIGRAPH V48EGR8807 graphite packing ring set provides reliable and long-lasting sealing in high-temperature and high-pressure environments. Thanks to its high-quality composition and advanced reinforcement technology, this gasket set can withstand the most demanding conditions, ensuring continuous and dependable operation. The graphite is enriched with passive inhibitors against corrosion and oxidation.

Applications

This Incobraid® graphite ring set is ideal for industrial valves used in steam, gas, and most chemical and petroleum services. It is particularly suitable for high-temperature and high-pressure environments, offering a reliable and durable solution for a variety of industrial applications, excluding situations involving strong oxidants.

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	рН	T°C	T°F
ı.	500	1		200	0 ÷ 14	-200 ÷ 450 / 650	-330 ÷ 840 / 1200



With weakly oxidizing agents and hot air the temperature must be limited to 450 $^\circ$ C With steam and non-oxidizing fluids the temperature must be limited to 650 $^\circ$ C

Graphite and carbon cannot be used with oxidizing fluids



PLANIGRAPH V48EGR8807

The PLANIGRAPH V48EGR8807 is a graphite packing ring set designed to ensure optimal performance in hightemperature and high-pressure industrial environments. Its high-quality composition offers a reliable and durable solution for a variety of industrial applications.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.,

Via Provinciale 1/E - 25030 Adro - BS - Italia tel. +39 030 7451121 / fax +39 030 7451130 www.carrara.it - info@carrara.it