



PLANIGRAPH V48Z OXYGEN BAM

Composition

Pure flexible graphite

Characteristics

PLANIGRAPH V48Z OXYGEN rings ensure safe and reliable performance in environments with liquid and gaseous oxygen. Certified according to BAM specifications, they provide effective protection against oxidation. When used in stems, assistance from GR80SGR OXYGEN braided wiper rings (BAM report 2-28/2015E) or PLANIGRAPH V48ZN OXYGEN nickel-reinforced graphite rings (BAM report 2-1948/2014E) is recommended.

Applications

Made with highly pure graphite, PLANIGRAPH V48Z OXYGEN expanded graphite rings offer high quality and reliability for applications involving liquid and gaseous oxygen.

Tech Data

Maximum Temperature C°	Maximum Oxygen Pressure bar
up to 60	420
> 60 to 280	250

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- The dimensional tolerances of the molded products refer to the Carrara Spa standard, unless otherwise agreed.



PLANIGRAPH V48Z OXYGEN BAM

PLANIGRAPH V48Z OXYGEN graphite rings are BAM certified for use with both liquid and gaseous oxygen. These expanded graphite rings are designed for services involving liquid and gaseous oxygen (BAM report 2-1949/2014 E), serving for stem or as fire-safe seals for closures and as packing for ball valve seats.

Report		BAM Bundesanstalt für Materialforschung und -prüfung
on Testing a Nonmetallic Material for Reactivity with Oxygen		
Reference Number	2-1949/2014 E	TEST REPORT
Copy	1. Copy of 2 Copies	
Customer	CARRARA S.p.A. Via Provinciale 1/E 25030 Adro (BS) Italy	
Order Date	August 4, 2014	
Reference	Order No: 1411295	
Receipt of Order	August 11, 2014	
Test Samples	Die-formed flexible graphite ring Planigraph ZV48Z OXY, undiluted batch, for use as a sealing material in piping, valves and fittings or other components for gaseous oxygen service at temperatures up to 280 °C and for liquid oxygen service. BAM Order No.: 2-1952/200	
Receipt of Samples	August 7, 2014	
Test Date	August 22, 2014 to February 6, 2015	
Test Location	BAM - Working Group "Safe Handling of Oxygen", building no. 41, room no. 073 and no. 120	
Test Procedure or Requirement According to	DIN EN 1297-2002-02 "Cryogenic Vessels - Gas/Material Compatibility" ISO 21015:2004-07 "Cryogenic Vessels - Gas/Material Compatibility" Annex of prEN 1297-2002-02 List of nonmetallic materials compatible with oxygen by BAM Federal Institute for Material Research and Testing, by Forschungsgesellschaft für Risiko- und chemische Industrie, Edition: March 2014. TIGS: 407 Technical Rules for Hazardous Substances "Fähigkeiten mit Gasen - Gefährdungsbeurteilung" chapter 3 "Informationsvermittlung und Gefährdungsbeurteilung" and chapter 4 "Stützmaßnahmen bei Tätigkeiten mit Gasen" Edition: June 2013	
<small>All pressures of this report are excess pressures. This test report consists of page 1 to 5 and annex 1 to 4. The test report may only be published or used for promotional purposes if it contains the information that it is a test report from BAM for an independent organization of this certificate of the publication of the test results. The test results are available in the test report. In case of a German version of the test report to be published, the German version is binding.</small>		
<small>M Safety in technology and chemistry</small>		



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it