

PTFE JOINTING SHEET PLANIFLON™ BO3

Tech Data

Planiflon™ B03			
Colour			Black
Filler			Graphite
Gravity	ASTM D792	g/cm3	1.95 - 2.10
Coefficient of linear thermal expansion	ASTM D696	10-5 (mm/mm)/°C	6.5 - 10
Hardness Shore D	ASTM D2240	Punti	≥ 65
Tensile strength	ISO 527 v=50mm/min	N/mm2	≥ 8
Elongation at break	ISO 527 v=50mm/min	%	≥ 40
Compressive strength at 1% strain	ASTM D695	N/mm2	12 - 13.5
Deformation under load (24 h 13.7 N/mm2 23°C)	ASTM D621	%	≤ 6
Permanent deformation	ASTM D621	%	≤ 1.5
Coefficient of dynamic friction	ASTM D1894	-	0.12
Wear factor at PV 100	ASTM D3702	-	20 - 30

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures Other gasketing sheet dimensions and thicknesses are available on request
- The dimensional tolerances of the gasketing sheets are: W and L \pm 3,0%, H \pm 10,0%

Size	1.500 x 1.500 - 1200 X 1200 - 600 x 600	60" x 60" - 48" x 48" - 24" x 24"
Thickness	0,75 ÷ 6,00	1/32" ÷ 1/4"



PTFE Jointing Sheet Planiflon™ BO3

The bidirectional structured PTFE gasketing sheets Planiflon™ are made with special resins and inorganic fillers. The special processing technique minimizes the material's cold flow, giving to the sheets the characteristic attribute of bidirectionality. The product range of the Planiflon™ includes the following products:

- B13 Modified PTFE with silica filler
- B14 Modified PTFE with hollow glass microspheres filler
- B15 Modified PTFE with barium sulphate filler
- B58 Microcellular Modified PTFE layers with pure modified PTFE core
- **B60** Microcellular Modified PTFE with Inorganic fillers
- **E12** Bi-directional expanded **PTFE**
- B01 Virgin PTFE
- B02 Glass filled PTFE
- B03 Graphite filled PTFE
- B05 Carbographite filled PTFE



