PTFE JOINTING SHEET PLANIFLON™ B60

Composition

- Microcellular modified PTFE
- Inorganic fillers

Characteristics

The Planiflon™ range has been developed to operate from cryogenic temperatures up to 260°C and can be used with all the most aggressive fluids (ph 0-14). Planiflon™ B60 is a gasketing sheet that shows an excellent chemical resistance, with excellent gas permeability. These gaskets are suitable both for metallic and non metallic flanges.

Applications

Planiflon™ B60 is suitable for industrial applications for sealing the flanges and has the following certificates:

- TA LUFT
- FDA
- DVGW

Tech Data

Planiflon™ B60			
Colour			White
Filler			Inorganic
Density		g/cm³	0,85
Temperature		°C	-200/+260
Max operating pressure		Bar	80
P x T max		Bar x °C	-
thickness 0,5 to 2,0			12000
thickness 3,0			8500
Compression	DIN 3535-6	%	>55
Creep	DIN 3535-6	%	<12
Recovery	DIN 3535-6	%	>5
Leakage	DIN 3535-6	mg*s-1*m-1	<0,002
PH Range			0 ÷ 14

- Never use the product at its maximum rated temperature and pressure simultaneously. Consult the manufacturer for further information.
- The peak temperature can be sustained only for short exposure periods.
- Other gasketing sheet dimensions and thicknesses are available on request.
- The dimensional tolerances of the gasketing sheets are: W and L ±3.0%, H ±10.0%.

Size	1.500 x 1.500	60” x 60”
Thickness	0.75 ÷ 6.0	1/32 ÷ 1/4

PTFE Jointing Sheet Planiflon™ B60

The bidirectional structured PTFE gasketing sheets Planiflon™ are made with special resins and inorganic fillers. The special processing technique minimizes the material's cold flow, giving to the sheets the characteristic attribute of bidirectionality. The product range of the Planiflon™ includes the following products:

- **B13** - Modified PTFE with silica filler
- **B14** - Modified PTFE with hollow glass microspheres filler
- **B15** - Modified PTFE with barium sulphate filler
- **B58** - Microcellular Modified PTFE layers with pure modified PTFE core
- **B60** - Microcellular Modified PTFE with Inorganic fillers
- **E12** - Bi-directional expanded PTFE

The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.

CARRARA GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 carrara.it - info@carrara.it