



PTFE JOINTING SHEET PLANIFLON™ B60

Composition

- Microcellular modified PTFE
- Inorganic fillers

Characteristics

The Planiflon™ range has been developed to operate from cryogenic temperatures up to 260°C and can be used with all the most aggressive fluids (ph 0-14). Planiflon™ B60 is a gasketing sheet that shows an excellent chemical resistance, with excellent gas permeability. These gaskets are suitable both for metallic and non metallic flanges.

Applications

Planiflon™ B58 is suitable for industrial applications for sealing the flanges and has the following certificates:


- TA LUFT
- FDA
- DVGW

Tech Data

Planiflon™ B60			
Colour			White
Filler			Inorganic
Density		g/cm ³	0,85
Temperature		°C	-200/+260
Max operating pressure		Bar	80
P x T max		Bar x °C	-
thickness 0,5 to 2,0			12000
thickness 3,0			8500
Compression	DIN 3535-6	%	>55
Creep	DIN 3535-6	%	<12
Recovery	DIN 3535-6	%	>5
Leakage	DIN 3535-6	mg*s-1*m-1	<0,002
PH Range			0 ÷ 14
Tolerances L and W		mm	+/- 50
Tolerances Thickness		%	+/-10

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- Other gasketing sheet dimensions and thicknesses are available on request

Size	1.500 x 1.500	60" x 60"
Thickness	0.8 ÷ 6.0	1/32 ÷ 1/4



PTFE Jointing Sheet Planiflon™ B60

The bidirectional structured PTFE gasketing sheets Planiflon™ are made with special resins and inorganic fillers. The special processing technique minimizes the material's cold flow, giving to the sheets the characteristic attribute of bidirectionality. The product range of the Planiflon™ includes the following products:

- **B13** - Modified PTFE with silica filler
- **B14** - Modified PTFE with hollow glass microspheres filler
- **B15** - Modified PTFE with barium sulphate filler
- **B58** - Microcellular Modified PTFE layers with pure modified PTFE core
- **B60** - Microcellular Modified PTFE with Inorganic fillers
- **E12** - Bi-directional expanded PTFE



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it