



EGPTFE PACKING GL7000

Composition

ePTFE yarns with encapsulated graphite and silicone lubricant.



Characteristics

The compression packing for dynamic services style GL7000 is made with pure egPTFE yarns filled with graphite. The encapsulation of the graphite in the expanded PTFE reduces the its migration and mitigates the thermal expansion of the sealing, common to all PTFE packing.

Applications

The egPTFE packing style GL7000 is recommended for all dynamic industrial applications. It is an excellent general purpose sealing suitable for all fluids with the exception of the strong oxidizers and those not compatible with the PTFE and the graphite. Its high elasticity and flexibility allow it to adapt perfectly to flanges and irregular surfaces, ensuring a secure and long-lasting seal. The compression packing style GL7000 is flexible, elastic, easy to cut and install. It is a universal braided packing egPTFE for pumps, agitators and mixers that provides reliable service and moderate shaft wear.

Tech Data

| | P bar | lbf/in2 | Vm/S | f/pm | pH | T°C | T°F |
|---|-------|---------|------|------|--------|------------|------------|
|  | 200 | 3000 | 2 | 400 | 0 ÷ 14 | -200 ÷ 280 | -330 ÷ 540 |
|  | 50 | 750 | 25 | 5000 | | | |

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- Graphite and carbon cannot be used with oxidizing fluids



egPTFE Packing GL7000

The family of the PTFE articles include a wide range of braided packings that can cover all applications that require the use of this material. The PTFE yarn is commonly used in gland sealing systems, both in static and dynamic applications, thanks to the properties of this material, which ensures efficient and reliable sealing that can cover almost the entire pH range. The packings are available in both dry and lubricated configuration, in combination with other fibers such as aramid or with a rubber core.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



EGPTFE PACKING GL7000

| Sezione mm | Sezione inch | Kg/box | Lbs/box | Mt/box | Ft/box | Mt/kg | Ft/lbs |
|------------|--------------|--------|---------|--------|--------|-------|--------|
| 3 | 1/8" | 1 | 2.2 | 50.0 | 164.0 | 50.0 | 74.5 |
| 4 | - | 1 | 2.2 | 33.3 | 109.3 | 33.3 | 49.6 |
| 5 | 3/16" | 1 | 2.2 | 25.0 | 82.0 | 25.0 | 37.2 |
| 6 | - | 2.5 | 5.5 | 41.7 | 136.8 | 16.7 | 24.8 |
| 6.5 | 1/4" | 2.5 | 5.5 | 35.7 | 117.1 | 14.3 | 21.3 |
| 8 | 5/16" | 2.5 | 5.5 | 25.0 | 82.0 | 10.0 | 14.9 |
| 9.5 | 3/8" | 2.5 | 5.5 | 17.9 | 58.7 | 7.1 | 10.7 |
| 10 | - | 2.5 | 5.5 | 15.6 | 51.2 | 6.3 | 9.3 |
| 11 | 7/16" | 2.5 | 5.5 | 13.2 | 43.3 | 5.3 | 7.9 |
| 12 | - | 2.5 | 5.5 | 10.9 | 35.8 | 4.3 | 6.5 |
| 12.7 | 1/2" | 2.5 | 5.5 | 10.4 | 34.1 | 4.2 | 6.2 |
| 14 | 9/16" | 5 | 11 | 16.1 | 52.8 | 3.2 | 4.8 |
| 16 | 5/8" | 5 | 11 | 12.5 | 41.0 | 2.5 | 3.7 |
| 17.5 | - | 5 | 11 | 10.8 | 35.4 | 2.2 | 3.2 |
| 18 | 11/16" | 5 | 11 | 9.6 | 31.5 | 1.9 | 2.9 |
| 19 | 3/4" | 5 | 11 | 8.5 | 27.9 | 1.7 | 2.5 |
| 22 | 7/8" | 5 | 11 | 6.8 | 22.3 | 1.4 | 2.0 |
| 25.5 | 1" | 5 | 11 | 5.3 | 17.4 | 1.1 | 1.6 |

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it