



ARAMIDIC EGPTFE PACKING GL7676

Composition

- Aramid yarns
- ePTFE yarns with encapsulated graphite and silicone lubricant



Characteristics

The style GL7676 is a special packing produced with an innovative braiding technique. It is made with egPTFE and aramid yarns combined in the "zebra" mode. This configuration improves the packing's resistance to the extrusion and it is able to reduce the wear of the sealing.

Applications

GL7676 is the packing for dynamic applications for all services with industrial fluids compatible with graphite, PTFE, and aramid fiber. The GL7676 packing is made with two yarns braided in a "zebra" pattern to create a braid whose properties are intended to combine the main characteristics of both: the toughness of aramid and the versatility of egPTFE. The GL7676 packing has shown particular suitability for use in pumps intended for slurry, for pumping water for industrial use in filtration and demineralization cycles.

Tech Data

| | P bar | lbf/in2 | Vm/S | f/pm | pH | T°C | T°F |
|---|-------|---------|------|------|--------|------------|------------|
|  | 250 | 3750 | 3 | 600 | 3 ÷ 12 | -100 ÷ 250 | -150 ÷ 480 |
|  | 50 | 750 | 25 | 5000 | | | |

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- The peak temperature can be sustained only for short exposure periods.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.



Aramidic egPTFE Packing GL7676

The family of the PTFE articles include a wide range of braided packings that can cover all applications that require the use of this material. The PTFE yarn is commonly used in gland sealing systems, both in static and dynamic applications, thanks to the properties of this material, which ensures efficient and reliable sealing that can cover almost the entire pH range. The packings are available in both dry and lubricated configuration, in combination with other fibers such as aramid or with a rubber core.



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.



Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 www.carrara.it - info@carrara.it



ARAMIDIC EGPTFE PACKING GL7676

| sezione mm | sezione inch | kg/box | lbs/box | mt/box | ft/box | mt/kg | ft/lbs |
|------------|--------------|--------|---------|--------|--------|-------|--------|
| 3 | 1/8" | 1 | 2.2 | 50.0 | 164.0 | 50.0 | 74.5 |
| 4 | - | 1 | 2.2 | 33.3 | 109.3 | 33.3 | 49.6 |
| 5 | 3/16" | 1 | 2.2 | 25.0 | 82.0 | 25.0 | 37.2 |
| 6 | - | 2.5 | 5.5 | 50.0 | 164.0 | 20.0 | 29.8 |
| 6.5 | 1/4" | 2.5 | 5.5 | 39.1 | 128.3 | 15.6 | 23.3 |
| 8 | 5/16" | 2.5 | 5.5 | 25.0 | 82.0 | 10.0 | 14.9 |
| 9.5 | 3/8" | 2.5 | 5.5 | 17.9 | 58.7 | 7.1 | 10.7 |
| 10 | - | 2.5 | 5.5 | 16.7 | 54.8 | 6.7 | 10.0 |
| 11 | 7/16" | 2.5 | 5.5 | 13.9 | 45.6 | 5.6 | 8.3 |
| 12 | - | 2.5 | 5.5 | 11.4 | 37.4 | 4.5 | 6.8 |
| 12.7 | 1/2" | 2.5 | 5.5 | 10.4 | 34.1 | 4.2 | 6.2 |
| 14 | 9/16" | 5 | 11 | 17.2 | 56.4 | 3.4 | 5.1 |
| 16 | 5/8" | 5 | 11 | 13.2 | 43.3 | 2.6 | 3.9 |
| 17.5 | - | 5 | 11 | 11.5 | 37.7 | 2.3 | 3.4 |
| 18 | 11/16" | 5 | 11 | 10.0 | 32.8 | 2.0 | 3.0 |
| 19 | 3/4" | 5 | 11 | 9.3 | 30.5 | 1.9 | 2.8 |
| 22 | 7/8" | 5 | 11 | 7.4 | 24.3 | 1.5 | 2.2 |
| 25.5 | 1" | 5 | 11 | 5.7 | 18.7 | 1.1 | 1.7 |

● The weight per meter and the packaging weight may have a tolerance of $\pm 10\%$. Other sizes and packaging options are available on request.



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not exactly represent the product, its color and/or marking.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 www.carrara.it - info@carrara.it