



DINAWHITE B1204

Composition

- Viscose technical yarns
- Dispersion of PTFE
- Inert lubricant

Characteristics

The fibers of the compression packing B1204 have an excellent chemical resistance (pH 1 ÷ 14). For this reason B1204 can be used both in the cellulose production process, where a greater chemical resistance is required, and in the other general services of the paper mill. B1204 is extremely soft thanks to the exclusive three-stage lubrication with PTFE which further reduces the friction of the packing. B1204 Dinawhite is a universal packing for paper mills that uses a composite fiber with very high mechanical resistance (tensile strength 27,000 Kg / cm²) with a low coefficient of friction, which reduces the abrasion up to 1 / 10 of the aramid fibers, increasing the life cycle of the braided packing.

Applications

The packing B1204 is specific for dynamic services with abrasive products and slurry pumps.


- Simple to use, easy to cut and install
- It allows a better regulation of the minimum lubrication during the exercise
- It is stronger than aramid fiber packing for high speed abrasive applications
- It is white and therefore eliminates the risk of contamination
- It does not wear out the shaft sleeves



DINAWHITE B1204

The compression packing Dinawhite B1204 is designed for dynamic sealing services with abrasive fluids and it is able to offer an exceptional performance thanks to its special fiber.

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	20	300	15	300	1 ÷ 14	÷ 100	÷ 212

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



DINAWHITE B1204

section mm	size inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8	1	2.2	74.1	243	74.1	110.3
4	-	1	2.2	41.7	137	41.7	62.1
5	3/16	1	2.2	26.7	87	26.7	39.7
6	-	2.5	5.5	46.3	152	18.5	27.6
6.5	1/4	2.5	5.5	39.4	129	15.8	23.5
8	5/16	2.5	5.5	26	85	10.4	15.5
9.5	3/8	2.5	5.5	18.5	61	7.4	11
10	-	2.5	5.5	16.7	55	6.7	9.9
11	7/16	2.5	5.5	13.8	45	5.5	8.2
12	-	2.5	5.5	11.6	38	4.6	6.9
12.7	1/2	2.5	5.5	10.3	34	4.1	6.2
14	9/16	5	11	17	56	3.4	5.1
16	5/8	5	11	13	43	2.6	3.9
17.5	11/16	5	11	10.9	36	2.2	3.2
18	-	5	11	10.3	34	2.1	3.1
19	3/4	5	11	9.2	30	1.8	2.8
22	7/8	5	11	6.9	23	1.4	2.1
25.5	1	5	11	5.1	17	1	1.5

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication and otherwise provided to users is based on experience and is provided to the best of our current knowledge. Due to many factors which are beyond our knowledge and control affecting the use of the products, no warranties are given or are to be held implied with respect to such information. The operating limits shown in this publication do not constitute a statement that these values can be applied simultaneously. Do not use the product at the associated maximum temperature and pressure values. The maximum temperature can be sustained for short exposures in particular conditions. Specifications are subject to change without notice.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it