

GR80SGR OXYGEN BAM

Composition

Expanded pure mineral graphite with special nickel-alloy reinforcement

Characteristics

The GR80SGR OXYGEN BAM gasket is a high-quality product made with pure expanded graphite yarn and produced through a contamination-free process. This gasket is flexible and exhibits excellent aging resistance when exposed to pure oxygen at 300°C and 220 bar pressure. Additionally, tests conducted on aged samples have shown that the gasket does not exhibit auto-ignition up to a temperature of 500°C. These characteristics make the GR80SGR OXY an ideal choice for applications that require high temperature and pressure resistance in the presence of pure oxygen.

Applications

The GR80SGR OXYGEN BAM gasket is specifically designed for oxygen service and intended for use in maintaining valves used in this type of service, but it can also be used for valves that require its high-performance features. It complies with the weight loss requirements established by the EN 14772 standard, section 6.7 and meets the safety requirements specified by the BAM certificate (report no. 2-952/2014E).

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	рН	Т°С	T°F	
產	220	3300	1	200	0 ÷ 14	-200 ÷ 300	-330 ÷ 570	

The maximum indicated temperature of 300°C refers to the use of the product with a fluid containing 100% oxygen. For fluids with a lower
oxygen content, the product can be used at higher temperatures. In such cases, consult the Carrara Technical Office for further information.



GR80SGR OXYGEN BAM

Carrara's graphite packing range offers a complete set of solutions designed to meet various application needs, using all the main types of graphite yarn available today. The range stands out for the quality of its materials and for the presence of corrosion inhibitors, developed to ensure greater durability and reliability over time. Carrara provides tailored solutions for every performance level: from industrial-grade products for standard applications to performer and premium lines designed for more demanding uses where efficiency and reliability are essential. Each packing is engineered to best fit the specific application, helping improve sealing performance and reduce operational costs. Visit our

Compression Packing Stock page. Carrara offers a wide range of sizes and materials available for immediate shipment.







GR80SGR OXYGEN BAM

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8"	1	2.2	52.6	172.6	52.6	78.4
4	-		2.2	41.7	136.8	41.7	62.1
5	5 3/16"		2.2	26.3	86.3	26.3	39.2
6	-	2.5	5.5	46.3	151.9	18.5	27.6
6.5	1/4"	2.5	5.5	39.7	130.2	15.9	23.6
8	5/16"	2.5	5.5	26.0	85.3	10.4	15.5
9.5	3/8"	2.5	5.5	18.5	60.7	7.4	11.0
10	-	2.5	5.5	16.7	54.8	6.7	10.0
11	7/16"	2.5	5.5	14.3	46.9	5.7	8.5
12	-	2.5	5.5	11.6	38.1	4.6	6.9
12.7	1/2"	2.5	5.5	10.4	34.1	4.1	6.2
14	9/16"	5	11	17.0	55.8	3.4	5.1
16	5/8"	5	11	13.2	43.3	2.6	3.9
17.5	-	5	11	11.9	39.0	2.4	3.5
18	11/16"	5	11	10.6	34.8	2.1	3.2
19	3/4"	5	11	10.3	33.8	2.1	3.1
22	7/8"	5	11	6.9	22.6	1.4	2.1
25.5	1"	5	11	5.3	17.4	1.1	1.6



The weight per meter and the packaging weight may have a tolerance of ±10%. Other sizes and packaging options are available on request.



