



VALVE PACKING GR80SGR OXYGEN BAM

Composition

Expanded pure mineral graphite with special nickel-alloy reinforcement


Characteristics

The GR80SGR OXYGEN BAM gasket is a high-quality product made with pure expanded graphite yarn and produced through a contamination-free process. This gasket is flexible and exhibits excellent aging resistance when exposed to pure oxygen at 300°C and 220 bar pressure. Additionally, tests conducted on aged samples have shown that the gasket does not exhibit auto-ignition up to a temperature of 500°C. These characteristics make the GR80SGR OXY an ideal choice for applications that require high temperature and pressure resistance in the presence of pure oxygen.

Applications

The GR80SGR OXYGEN BAM gasket is specifically designed for oxygen service and intended for use in maintaining valves used in this type of service, but it can also be used for valves that require its high-performance features. It complies with the weight loss requirements established by the EN 14772 standard, section 6.7 and meets the safety requirements specified by the BAM certificate (report no. 2-952/2014E).

Tech Data

	P bar	lbf/in ²	Vm/S	f/pm	pH	T°C	T°F
	220	3300	1	200	0 ÷ 14	-200 ÷ 300	-330 ÷ 570

- The maximum indicated temperature of 300°C is related to the use of the product with a fluid 100% oxygen. For fluids with lower oxygen content, the product can be used at higher temperatures. In this case, consult the Carrara technical office for further information.



Valve Packing GR80SGR OXYGEN BAM

The Carrara graphite gland packing product range includes items made with all available graphite yarns, which, according to ASTM F2191 classification, are Type I—Continuous yarn, Type II—Staple yarn, and Type III—Flexible yarn. All graphite gland packings are protected with passive or active corrosion inhibitors (Grade A—Treated with corrosion inhibitor), although untreated gland packings (Grade B—No corrosion inhibitor) are available on demand. The performer and premium grade product ranges include Class 2 items, while the Industrial grade product range offers Class 1 products. Carrara graphite gland packings are specialized for each application, and a proper selection of the item allows for maximizing the sealing performance while reducing the component management costs.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



VALVE PACKING GR80SGR OXYGEN BAM

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8"	1	2.2	52.6	172.6	52.6	78.4
4	-	1	2.2	41.7	136.8	41.7	62.1
5	3/16"	1	2.2	26.3	86.3	26.3	39.2
6	-	2.5	5.5	46.3	151.9	18.5	27.6
6.5	1/4"	2.5	5.5	39.7	130.2	15.9	23.6
8	5/16"	2.5	5.5	26.0	85.3	10.4	15.5
9.5	3/8"	2.5	5.5	18.5	60.7	7.4	11.0
10	-	2.5	5.5	16.7	54.8	6.7	10.0
11	7/16"	2.5	5.5	14.3	46.9	5.7	8.5
12	-	2.5	5.5	11.6	38.1	4.6	6.9
12.7	1/2"	2.5	5.5	10.4	34.1	4.1	6.2
14	9/16"	5	11	17.0	55.8	3.4	5.1
16	5/8"	5	11	13.2	43.3	2.6	3.9
17.5	-	5	11	11.9	39.0	2.4	3.5
18	11/16"	5	11	10.6	34.8	2.1	3.2
19	3/4"	5	11	10.3	33.8	2.1	3.1
22	7/8"	5	11	6.9	22.6	1.4	2.1
25.5	1"	5	11	5.3	17.4	1.1	1.6

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it