



CARBOGRAPH PACKING INCOBRAID® C8207

Composition

Special PAN carbonized staple carbon yarns, blended with thousand of thin discontinuous metal fibres, impregnated with graphite and corrosion inhibitor.

Characteristics

Incobraid® C8207 is the compression packing braided with special carbonized staple carbon yarns impregnated in three stages, on the single yarn, during the braiding and on the body, with a mixture rich of graphite and inorganic corrosion inhibitor. Incobraid® C8207 is flexible, easy to install and guarantees the sealing thanks to its exceptional recovery.

Applications

The compression packing Incobraid® C8207 is recommended for industrial valves in high temperature steam and hydrocarbons-chemicals services, with the exception of strong oxidants and fluids incompatible with graphite.



Carbograph Packing INCOBRAID® C8207

The compression packing Incobraid® includes the styles GR8807 and C8207. These packings are braided with the yarns, respectively graphitized and carbonized staple carbon yarns, based on the blending yarns technology. Incobraid® mixes the carbon fibers with thousand of discontinuous thin metal fibers. Finally, the metal content of the Incobraid® yarns is 25% by weight but they also retain a great flexibility and workability like the unreinforced yarns.

Tech Data

	P bar	lbf/in2	Vm/S	f/pm	pH	T°C	T°F
	200	3000	1	200	2 ÷ 12	-100 ÷ 350 / 500	-150 ÷ 660 / 940
	80	1200	2	400			

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- The peak temperature can be sustained for short exposures
- Graphite and carbon cannot be used with oxidizing fluids



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Carrara S.p.A.
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it



CARBOGRAPH PACKING INCOBRAID® C8207

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3	1/8"	1	2.2	100.0	328.1	100.0	149.0
4	-	1	2.2	50.0	164.0	50.0	74.5
5	3/16"	1	2.2	33.3	109.3	33.3	49.6
6	-	2.5	5.5	62.5	205.1	25.0	37.2
6.5	1/4"	2.5	5.5	50.0	164.0	20.0	29.8
8	5/16"	2.5	5.5	35.7	117.1	14.3	21.3
9.5	3/8"	2.5	5.5	25.0	82.0	10.0	14.9
10	-	2.5	5.5	22.7	74.5	9.1	13.5
11	7/16"	2.5	5.5	19.2	63.0	7.7	11.4
12	-	2.5	5.5	15.6	51.2	6.3	9.3
12.7	1/2"	2.5	5.5	13.9	45.6	5.6	8.3
14	9/16"	5	11	22.7	74.5	4.5	6.8
16	5/8"	5	11	17.9	58.7	3.6	5.3
17.5	-	5	11	15.6	51.2	3.1	4.6
18	11/16"	5	11	13.9	45.6	2.8	4.1
19	3/4"	5	11	12.5	41.0	2.5	3.7
22	7/8"	5	11	10.4	34.1	2.1	3.1
25.5	1"	5	11	7.9	25.9	1.6	2.4

- The weight per meter and the packaging's weight may have a tolerance of +/- 10%. Other sizes and packaging are available on demand.



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it