

COMPRESSED FIBER GASKETS PLANIFLEX™ PF41

Composition

Organic fiber NBR binder.

Characteristics

The compressed fiber gasketing sheets Planiflex™ PF41 are the greatest material for general applications. Economic, secure, tested.

Applications

Planiflex[™] PF41 can be applied continuously in the temperature range -40°C÷120°C and in the pressure ranges up to ratings 600 lbs and PN40. These gaskets show typical chemical compatibility in the middle of the pH range.

Properties thickness 1,5 mm	Unit	Value
Binder		NBR
Compressibility ASTM F 36	%	9
Recovery ASTM F 36	%	60
Tensile strength DIN 52910	N/mm2	8
Density +/- 5%	g/cm3	1,8
Stress re	sistance DIN 52913	
16 h, 300 °C, 50 N/mm2	N/mm2	
16 h, 175 °C, 50 N/mm2	N/mm2	20
Thickness inc	rease acc.to ASTM F 146	
Oil IRM 903, 5 h, 150 °C	%	10
ASTM Fuel B, 5 h, 23 °C	%	10
Distilled water. 5h. 100°C	%	4
Max. op	erating conditions	
Peak temperature	°C	180
Continuous temperature	°C	140
Continuous temperature with steam	°C	120
Pressure	bar	40



Compressed fiber gaskets Planiflex[™] PF41

The Planiflex[™] gasketing sheets are made with materials based on aramid fibers and NBR specially selected for meet high performance standards for a wide range of industrial applications. Planiflex[™] gaskets are applicable for seal with vapors, lubricants, solvents, gases, steam and many diluted acids and alkalis and can be used as a gasket together with PTFE envelopes.

Do not use the product at maximum temperature values or under pressures higher than those typical of flue gases. Consult the manufacturer • for further informatior

Size	1.500 × 1.500 1.500 × 3.000	60" × 60" 60" × 120"
Thickness	0.5 ÷ 5.0	1/64" ÷ 7/32"



Carrara S.p.A.,

Via Provinciale 1/E - 25030 Adro - BS - Italia tel. +39 030 7451121 / fax +39 030 7451130 www.carrara.it - info@carrara.it



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.