



CONTROLLER ONE Z

Composition

- **Graphite Rings V48Z:** Pure nuclear-grade graphite PLANIGRAPH
- **Top & Bottom Rings GR 8807 INCOBRAID®:** Graphite P.A.N. reinforced with discontinuous NiCr microfilament, impregnated with pure graphite, inorganic corrosion inhibitor, and zinc

Characteristics

CONTROLLER ONE Z is entirely made of graphite, ensuring excellent chemical and thermal resistance. The special structure, with the presence of Incobraid® GR8807 as Top and Bottom, offers exceptional extrusion resistance, allowing for greater sealing with a lower clamping load. This makes it particularly suitable for applications with steam, gas, and most chemicals and petroleum products. However, use with strong oxidizers should be avoided.

Applications

Specifically designed for valves, CONTROLLER ONE Z is suitable for ensuring sealing in a wide range of industrial services, including those with steam, gas, and chemicals. Its extrusion resistance and ability to maintain sealing even with a lower clamping load make it a reliable choice for industrial applications.

Tech Data

| P bar | lbf/in ² | Vm/S | f/pm | pH | T°C | T°F |
|-------|---------------------|------|------|-----|--------|------------------|
| | 300 | 4500 | 1 | 200 | 0 ÷ 14 | -200 ÷ 450 / 650 |

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- The peak temperature can be sustained only for short exposure periods.
- With weakly oxidizing agents and hot air, the temperature must be limited to 450 °C.
- With steam and non-oxidizing fluids, the temperature must be limited to 650 °C.
- Flexible graphite and carbon yarns shall not be used with oxidizing fluids.



CONTROLLER ONE Z

The set of expanded graphite rings with trapezoidal section (Planigraph V48Z) with head and bottom in GR8807 INCOBRAID® graphite braid represents a reliable solution to ensure sealing in a wide range of industrial applications.



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not accurately represent the product's color and/or marking.



GLOBAL SEALING SOLUTIONS

Carrara S.p.A.

Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 www.carrara.it info@carrara.it