



PLANIGRAPH™ LGR

Composition

Flexible graphite C > 98,00% with smooth stainless steel core.

Characteristics

The LGR gaskets offer an excellent performances for sealing the bonnet flanges of the valves and for sealing the heat exchangers. Improved permeability resistance can be achieved with the inner eyelet. For a perfect seal with this gasket it is recommended to use a thickness of 1.5 mm.

Applications

Graphite gaskets for bonnet flanges and heat exchangers. The graphite doesn't work with oxidizing fluids.



Planigraph™ LGR

LGR is a gasketing expanded graphite sheet with smooth insertion. The maximum pressure for using these gaskets is strongly correlated to the gasket sealing surface. It is always suggested to calculate the ratio between [De-Di] and the thickness of the gasket, where De and Di refer to the effective diameters of the parts of the gasket compressed by the flanges. The ratio must be at least 4. In any case the maximum load allowed on the gasket is 60 Mpa. For sealing on WN RF flanges LGR gaskets are suitable until pressure class 300 psi. The maximum operating pressure pointed in the grid is only for reference because the maximum assembly load requirements must always be met in correlation to the temperature and the active sealing surface (EN 1591-2: 2020).

Tech Data

Planigraph™ LGR		
Graphite density	gr/cm3	1.0
Carbon Content	%	≥ 98.0
Ash Content	%	≤ 2.0
Sulphur Content	ppm	≤ 1000
Halogen Content	ppm	≤ 200
Reinforcing steel sheet	AISI	316L
Thickness steel sheet	mm	0.05
Tensile Strenght	MPa	≥ 4.0
Compressibility	%	40 - 50
Recovery	%	> 7
Relaxation stress DIN 52913	N/mm2	> 45
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196
Maximum assembly load RT	N/mm2	60
Maximum operating pressure	bar	75

- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- With weakly oxidizing agents and hot air the temperature must be limited to 450 °C
- Graphite and carbon cannot be used with oxidizing fluids
- With steam and non-oxidizing fluids, the temperature must be limited to 550°C
- The dimensional tolerances of the gasketing sheets are: W and L ± 3,0%, H ± 10,0%

Size	1.000 x 1.000 1.500 x 1.500	40" x 40" 60" x 60"
Thickness	0.5 ÷ 3.0	1/64" ÷ 1/8"



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it