



PLANIFLON PT2105

Composition

Modified PTFE

Characteristics

Key characteristics of the **Planiflon PT2105** include a specific gravity of 2.15 g/cm³, tensile strength of at least 28 N/mm², and elongation at break of at least 350%. The tensile modulus is at least 600 N/mm². Shrinkage is 3%, while deformation under load is 15%. The material is classified as V-0 for flammability and has a dielectric strength of 2.5 kV/mil. The service temperature range (general service) is from -200°C to 260°C. It is BAM approved for oxygen service.

Applications

The **Planiflon PT2105** is particularly suitable for applications requiring reliable sealing of stems and seats of industrial valves in sectors such as chemical, petroleum, and pharmaceutical. Suitable for high-pressure and extreme temperature applications.

Tech Data

Properties	Unit	Value
Specific gravity	g/cm ³	2,15
Tensile strenght	N/mm ²	≥ 28
Elongation	%	≥ 350
Tensile modulus	N/mm ²	≥ 600
Shrinkage	%	3
Compressive strength at 1% deformation	N/mm ²	4-5
Deformation under load (24h 15,0 N/mm ² 23°C)	%	15
Deformation under load (100h 15,0 N/mm ² 23°C)	%	17
Deformation under load (Permanent 15,0 N/mm ² 23°C)	%	11
Flammability		V-0
Melt point (initial)	°C	342 ± 10
Melt point (second)	°C	327 ± 10
Dielectric Strenght	kV/mil	2.5
Service Temperature Range (general service)	°C	-200 ÷ 260
BAM Approved for Oxygen Service	[°C ; Bar]	Suitable [60; 30] [200 ; 20]

- Never use the product at its maximum rated temperature and pressure. Consult the manufacturer for further information.
- The data reported in the technical sheet represent the average values of the product and may differ from those of the specific batch delivered.



PLANIFLON PT2105

The **Planiflon PT2105** is a **high-quality PTFE** for stem and seat sealing of industrial valves. The material exhibits high chemical resistance (except for alkalis and hydrofluoric acid) and is suitable for a wide range of pressure applications.

TEST REPORT
on Testing a Nonmetallic Material for Reactivity with Oxygen

Reference Number: 17034693 E
Our Reference: 02-3432
Copy: 1, copy of 2 copies
Customer: Carrara S.p.A.
Via Provinciale 1/E
25030 Adro (BS)
ITALY
Date of Request: June 19, 2017
Your Reference: PO No. 170675
Receipt of Signed Contract: August 6, 2017
Test Samples: PLANIFLON PT2105,
batch 170256
Receipt of Samples: June 27, 2017
Test Date: July 26, 2017 to September 15, 2017
Test Location: BAM - Division 2.1 „Gases, Gas Plants“
building no. 41
Test Procedure or Requirement According to: DIN EN 1259 und ISO 21070
"Creep Viscosity - Gas/Material Compatibility"
Annex of code of practice M 534 - (BCI 617-5)
"List of nonmetallic materials compatible with hydrogen" by German Social
Accident Insurance Institution for the non-metallic and chemical industry
TRGS 407 Technical Rules for Hazardous Substances
"Transport and Storage - Gefahrguttransport"
chapter 3 "Informationsermittlung und Gefährdungsbeurteilung" and
chapter 4 "Schutzmaßnahmen bei Gefährdungen von Leben"

All pressures of this report are excess pressures.
This test report consists of page 1 to 3 and annex 1 to 4.
This test report may only be published in full wording and without any additions. A reproducible version must be
be obtained from BAM (bundesanstalt für Materialforschung und -prüfung) for any intended reproduction or the publication of any excerpts. The content of
the test report refers exclusively to the object materials tested.
The German version is legally binding, except an English version is issued exclusively.
2019-08 / 2019-09-07
Issued in Technical and Chinese



The information provided in this publication, as well as that supplied to users in other forms, is based on our experience and communicated according to the best knowledge available. However, since numerous factors beyond our knowledge and control may influence the use of the products, no warranty, explicit or implicit, is given regarding such content. The operating limits indicated do not constitute confirmation that these values can be applied simultaneously. Avoid using the product at the maximum temperature and pressure limits. The maximum temperature is sustainable only for short periods under specific conditions. Specifications may be changed without notice. The images in the DS may not accurately represent the product's color and/or marking.

CARRARA
GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 www.carrara.it - info@carrara.it