



PLANIGRAPH™ LGRHDI

Composition

- Expanded Graphite Industrial Grade
- Multiple smooth SS316L inserts with a thickness of 0.05 mm

Characteristics

The Planigraph™ LGRHDI graphite gasketing sheets are suitable for high-temperature and high-pressure applications on RF, FF, LMF, and LTG flanges in piping or industrial machinery. Planigraph™ LGRHDI features low relaxation values combined with excellent mechanical strength.

Applications

The gaskets Planigraph™ LGRHDI are suitable for all flanges, including RF, FF, LMF, and LTG. Graphite cannot be used with oxidizing fluids. Dimensional tolerances of the sheets are +/-5.0%.

Tech Data

Planigraph™ LGRHDI

Graphite density	gr/cm3	1.0
Carbon Content	%	> 98.0
Ash Content	%	< 2.0
Material of insert	AISI	316L
Thickness of insert	mm	0.05
Compressibility	%	25 - 35
Recovery	%	> 15
Gas Permeability DIN 3535	cm3/min	< 0.6
Relaxation stress DIN 52913	N/mm2	> 45
Temperature max with steam	°C	550
Temperature max with weak oxidants	°C	450
Temperature min cryo	°C	-196
Maximum assembly load RT	N/mm2	200
Maximum operating pressure	bar	200

- With steam and non-oxidizing fluids, the temperature must be limited to 550°C
- Never use the product to the maximum temperature and pressure associated. Consult the manufacturer for further information
- With weakly oxidizing agents and hot air the temperature must be limited to 450 °C
- Graphite and carbon cannot be used with oxidizing fluids

Size	1000 x 1000 - 1500 x 1500	40"x40" - 60"x60"
Thickness	1.0 + 3.0	1/32 ÷ 1/8



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.



Planigraph™ LGRHDI

The graphite gasketing sheets Planigraph™ LGRHDI are reinforced with multiple metallic layers and are designed for high-pressure applications, although they can be successfully installed in all applications. The operating pressure of the gasket is strongly correlated with the sealing surface, and it is always advisable to verify the ratio between [De-Di] and the gasket thickness, where De and Di refer to the diameters of the gasket parts effectively engaged by the flange compression. The ratio must be at least 4, and in this case, the maximum compression allowed on the gasket is 200 MPa. The maximum exposed pressure is only indicative because the maximum assembly load requirements must always be met in correlation with the temperature and the active sealing surface (EN 1591-2:2020).


GLOBAL SEALING SOLUTIONS

Carrara S.p.A.,
Via Provinciale 1/E - 25030 Adro - BS - Italia
tel. +39 030 7451121 / fax +39 030 7451130
www.carrara.it - info@carrara.it