





TECHNICAL DATA SHEET - CST 0200/03 - 04/11/2013

PT 5504L

(*)				
T	°C	-200 +280		
p	bar		100	25
V	m/s		2	8
pH		0 ÷ 14		



Avoid the product's use at the maximum temperature and pressure value associated without consult the manufacturer

Composition

Pure PTFE multifilament yarns
 Impregnation with PTFE dispersion

Features

PT5504L, made by 100% PTFE multifilament yarns, is lubricated with special compound in order to reduce the coefficient and guarantee long life services.
 Suitable in the type PT5504AL for food contact services.

Applications

PT5504L is recommended for dynamic applications with pumps and mixers.

sezione mm	sezione inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3,0	1/8	1,0	2,2	58,5	192	58,5	87,1
4,0	-	1,0	2,2	32,9	108	32,9	49,0
5,0	3/16	1,0	2,2	21,1	69	21,1	31,4
6,0	-	2,5	5,5	36,5	120	14,6	21,8
6,5	1/4	2,5	5,5	31,1	102	12,5	18,6
8,0	5/16	2,5	5,5	20,6	67	8,2	12,2
9,5	3/8	2,5	5,5	14,6	48	5,8	8,7
10,0	-	2,5	5,5	13,2	43	5,3	7,8
11,0	7/16	2,5	5,5	10,9	36	4,3	6,5
12,0	-	2,5	5,5	9,1	30	3,7	5,4
12,7	1/2	2,5	5,5	8,2	27	3,3	4,9
14,0	9/16	5,0	11,0	13,4	44	2,7	4,0
16,0	5/8	5,0	11,0	10,3	34	2,1	3,1
17,5	11/16	5,0	11,0	8,6	28	1,7	2,6
18,0	-	5,0	11,0	8,1	27	1,6	2,4
19,0	3/4	5,0	11,0	7,3	24	1,5	2,2
22,0	7/8	5,0	11,0	5,4	18	1,1	1,6
25,5	1	5,0	11,0	4,0	13	0,8	1,2

Packaged +/- 10 % in weight. Customized sizes and packaging are available on demand